


Viscosity Conversion Table

Centipoise	Gardner Holdt Bubble	Krebs- Stormer KU	Saybolt Universal SSU	Ford Cup 3	Ford Cup 4	Zahn Cup 1	Zahn Cup 2	Zahn Cup 3	Zahn Cup 4	Zahn Cup 5
10	A4		60		5	30	16			
15	A3		80		8	34	17			
25	A2		130	15	12	41	19			
30	A1		160	19	14	44	20			
40	A		210	25	18	52	22			
60	B	33	320	33	25	68	27			
80	C	37	430	41	31		34			
100	D	40	530	50	34		41	12	10	
120	E	43	580	58	41		49	14	11	
140	F	46	690	66	45		58	16	13	
160	G	48	790		50		66	18	14	
200	H	52	1000		58		82	23	17	10
220	I	54	1100		62			25	18	11
240	J	56	1200		65			28	20	12
280	K	59	1380		70			32	22	14
300	L	60	1475		74			34	24	15
320	M		1530					36	25	16
340	N		1630					39	26	17
360	O	62	1730					41	28	18
400	P	64	1950					46	30	20
440	Q		2160					50	33	22
460	R	66	2270					52	34	23
500	S	68	2480					57	37	25
550	T	69	2660					63	40	27
600	U	71	2900					68	44	30
900	V	81	4300						64	45
1000	W	85	4600							49
1300	X	95	6100							64
1700	Y	101	8000							
2300	Z	105	10750							
2500	Z1	114	11600							
3500	Z2	129	16500							
4500	Z3	136	21000							
6000	Z4		28000							
10000	Z5		46500							
15000	Z6		69500							

Dianal America, Inc.

9675 Bayport Blvd.
Pasadena, TX 77507, USA
Phone +1 713-758-8100
Toll Free 800-776-3659
Fax +1 281-474-2757
www.dianal.com



Good Chemistry for Tomorrow

Mitsubishi Chemical Holdings Group

The recommendations, suggestions and date herein are believed to be accurate and reliable at the time of printing. Dianal America, Inc. does not represent, warrant or guarantee the completeness or reliability of the same, or the use of any of our products, either alone or in combination with others since conditions and methods of use of our products are beyond our control.